



Varenr.	Diameter		Size Circ.	Weight			Breaking Load		
	mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
-	24	1	3	405	40,5	27,2	8 770	19 333	86
	26	1 1/32	3 1/4	439	43,9	29,5	9 483	20 907	93
	28	1 1/8	3 1/2	473	47,3	31,8	10 197	22 481	100
	30	1 1/4	3 3/4	543	54,3	36,5	10 809	23 829	106
	32	1 5/16	4	614	61,4	41,3	12 237	26 977	120
	36	1 1/2	4 1/2	760	76	51,1	15 092	33 271	148
	40	1 5/8	5	950	95	63,8	18 865	41 589	185
	44	1 3/4	5 1/2	1 175	117,5	79	22 638	49 907	222
	48	2	6	1 364	136,4	91,7	26 003	57 326	255
	52	2 1/8	6 1/2	1 600	160	107,5	30 082	66 318	295
	56	2 1/4	7	1 850	185	124,3	34 467	75 984	338
	60	2 1/2	7 1/2	2 120	212	142,5	39 157	86 326	384
	64	2 5/8	8	2 420	242	162,6	44 154	97 341	433
	68	2 3/4	8 1/2	2 732	273,2	183,6	49 456	109 031	485
	72	2 7/8	9	3 060	306	205,6	52 618	116 000	516
	80	3 1/4	10	3 780	378	254	63 631	140 279	624
	88	3 5/8	11	4 570	457	307,1	76 173	167 930	747
	96	4	12	5 450	545	366,2	89 429	197 155	877
	104	4 1/4	13	6 400	640	430,1	102 278	225 480	1003
	112	4 5/8	14	7 400	740	497,2	117 166	258 302	1149
	120	5	15	8 500	850	571,2	133 277	293 821	1307
	128	5 1/4	16	9 640	964	647,8	147 044	324 170	1442
	136	5 1/2	17	10 930	1093	734,4	165 908	365 759	1627

Raw material: Spun

Polypropylene / Polyester

Specific Gravity: 1,16

Melting Point: 165°C / 265°C

Elongation at % of BS:

25% 3,5%

50% 7,9%