

Combo / 12 strands



Varenr.	Diameter		Size Circ.	Weight			Breaking Load		
	mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
-	24	1	3	319	31,9	21,4	10 911	24 054	107
	26	1 1/32	3 1/4	374	37,4	25,1	12 747	28 101	125
	28	1 1/8	3 1/2	434	43,4	29,2	14 684	32 372	144
	30	1 1/4	3 3/4	498	49,8	33,5	16 723	36 868	164
	32	1 5/16	4	566	56,6	38	18 967	41 814	186
	36	1 1/2	4 1/2	717	71,7	48,2	23 759	52 380	233
	40	1 5/8	5	885	88,5	59,5	29 062	64 070	285
	44	1 3/4	5 1/2	1 070	107	71,9	34 874	76 884	342
	48	2	6	1 270	127	85,3	41 197	90 822	404
	52	2 1/8	6 1/2	1 500	150	100,8	48 029	105 884	471
	56	2 1/4	7	1 730	173	116,2	55 371	122 070	543
	60	2 1/2	7 1/2	1 990	199	133,7	63 223	139 380	620
	64	2 5/8	8	2 270	227	152,5	71 482	157 589	701
	68	2 3/4	8 1/2	2 560	256	172	80 150	176 698	786

Raw material: Mixed Polyolefin / Polyester

Specific Gravity: 1,16 (sinks)

Melting Point: 165°C / 265°C

Elongation at % of BS:
 25% 3,2%
 50% 6,7%