

Combo /



Varenr.	Diameter		Size Circ.	Weight			Breaking Load		
	mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
-	24	1	3	279	27,9	18,7	9 820	21 649	96,3
	26	1 1/32	3 1/4	328	32,8	22	11 523	25 403	113
	28	1 1/8	3 1/2	380	38	25,5	13 256	29 225	130
	30	1 1/4	3 3/4	437	43,7	29,4	15 092	33 271	148
	32	1 5/16	4	497	49,7	33,4	17 029	37 543	167
	34	1 11/32	4 1/4	563	56,3	37,8	19 273	42 488	189
	36	1 1/2	4 1/2	629	62,9	42,3	21 414	47 209	210
	38	1 9/16	4 3/4	703	70,3	47,2	23 861	52 605	234
	40	1 5/8	5	776	77,6	52,1	26 207	57 775	257
	44	1 3/4	5 1/2	939	93,9	63,1	31 407	69 240	308
	48	2	6	1 110	111	74,6	37 118	81 829	364
	52	2 1/8	6 1/2	1 320	132	88,7	43 236	95 318	424
	56	2 1/4	7	1 520	152	102,1	49 864	109 930	489
	60	2 1/2	7 1/2	1 750	175	117,6	56 900	125 442	558
	64	2 5/8	8	1 990	199	133,7	64 344	141 853	631
	68	2 3/4	8 1/2	2 250	225	151,2	72 094	158 938	707
	72	2 7/8	9	2 520	252	169,3	80 456	177 372	789
	80	3 1/4	10	3 110	311	209	98 199	216 488	963
	90	3 9/16	11 1/8	3 930	393	264,1	123 692	272 690	1 213

**Raw material: Mixed
Polyolefin / Polyester**

Specific Gravity: 1,16

**Melting Point: 165°C /
265°C**

**Elongation at % of BS:
25% 4,0%
50% 7,0%**