

Movster / 8 strands



Diameter		Size Circ.	Weight			Breaking Load		
mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	kgf	lbf	kN
24	1	3	279	27,9	18,7	9 820	21 649	96,3
26	1 1/32	3 1/4	328	32,8	22	11 523	25 403	113
28	1 1/8	3 1/2	380	38	25,5	13 256	29 225	130
30	1 1/4	3 3/4	437	43,7	29,4	15 092	33 271	148
32	1 5/16	4	497	49,7	33,4	17 029	37 543	167
36	1 1/2	4 1/2	629	62,9	42,3	21 414	47 209	210
40	1 5/8	5	776	77,6	52,1	26 207	57 775	257
44	1 3/4	5 1/2	939	93,9	63,1	31 407	69 240	308
48	2	6	1 110	111	74,6	37 118	81 829	364
52	2 1/8	6 1/2	1 320	132	88,7	43 236	95 318	424
56	2 1/4	7	1 520	152	102,1	49 864	109 930	489
60	2 1/2	7 1/2	1 750	175	117,6	56 900	125 442	558
64	2 5/8	8	1 990	199	133,7	64 344	141 853	631
68	2 3/4	8 1/2	2 250	225	151,2	72 094	158 938	707
72	2 7/8	9	2 520	252	169,3	80 456	177 372	789
80	3 1/4	10	3 110	311	209	98 199	216 488	963
88	3 5/8	11	3 750	375	252	118 288	260 775	1 160
96	4	12	4 470	447	300,4	139 702	307 984	1 370
104	4 1/4	13	5 260	526	353,4	162 135	357 442	1 590
112	4 5/8	14	6 050	605	406,5	187 628	413 643	1 840
120	5	15	6 980	698	469	214 141	472 093	2 100
128	5 1/4	16	7 950	795	534,2	241 674	532 790	2 370
136	5 1/2	17	8 950	895	601,4	271 246	597 984	2 660

**Raw material: Mixed
Polyolefin / Polyester**

Specific Gravity: 1,00 (floats)

Melting Point: 165°C / 265°C

**Elongation at % of BS:
25% 3,9%
50% 8,3%**