



Varenr.	Diameter		Size Circ.	Weight			Breaking Load		
	mm	Inches	Inches	Ktex	Kg/100m	lbs/100ft	Kgf	lbf	kN
-	24	1	3	261	26,1	17,5	10 605	23 380	104
	26	1 1/32	3 1/4	306	30,6	20,6	12 339	27 202	121
	28	1 1/8	3 1/2	355	35,5	23,9	14 174	31 248	139
	30	1 1/4	3 3/4	408	40,8	27,4	16 112	35 519	158
	32	1 5/16	4	464	46,4	31,2	18 253	40 240	179
	36	1 1/2	4 1/2	587	58,7	39,4	22 842	50 357	224
	40	1 5/8	5	725	72,5	48,7	27 940	61 597	274
	44	1 3/4	5 1/2	877	87,7	58,9	33 345	73 512	327
	48	2	6	1 040	104	69,9	39 259	86 550	385
	52	2 1/8	6 1/2	1 220	122	82	45 683	100 713	448
	56	2 1/4	7	1 420	142	95,4	52 414	115 550	514
	60	2 1/2	7 1/2	1 630	163	109,5	59 450	131 062	583
	64	2 5/8	8	1 860	186	125	66 996	147 698	657
	68	2 3/4	8 1/2	2 100	210	141,1	75 153	165 682	737

Raw material: Mixed

Polyolefin (HT)

Specific Gravity: 0,94
(floats)

Melting Point: 165°C

Elongation at % of BS:
25% 2,8%
50% 5,5%